CX3199984 | 075G135PP200R0PE COEX



ConQuest® Empty Conduit, 3/4 in, SDR 13.5, gray, with pull rope

 *Product complies with the Build America, Buy America Act (BABAA) requirements of the Infrastructure Investment and Jobs Act of 2021 (Pub. L. 117- 58, §§ 70901-70953), or is the subject of a waiver approved by the Secretary of Commerce or designee. Compliance requirements and waiver applicability vary based on government funding program. Check the laws and regulations for your specific program.

Product Classification

Regional AvailabilityNorth AmericaProduct TypeEmpty conduitProduct BrandConQuest®

Government Requirements Build America Buy America (BABA) compliant*

General Specifications

Color Gray

Conduit Type Non-toneable

Density Test Method ASTM D792A

 Density, maximum
 0.955 g/cm³ | 0.035 lb/in³

 Density, minimum
 0.941 g/cm³ | 0.034 lb/in³

Design Standard ASTM D3350-05

Location of ManufacturingCatawba, North Carolina

Wall Type Smooth

Dimensions

 Length
 304.8 m | 1000 ft

 Inner Diameter, nominal
 22.2 mm | 0.874 in

 Outer Diameter, nominal
 26.67 mm | 1.05 in

Wall Thickness Designation SDR 13.5

Wall Thickness, minimum 1.981 mm | 0.078 in

Nominal Size 3/4 in

Material Specifications

Flexural Modulus, minimum 551.581 N/mm² | 80000 psi



CX3199984 | 075G135PP200R0PE COEX

Flexural Property Test Method ASTM D790

Hydrostatic Design BasisNot pressure rated

Hydrostatic Design Test MethodASTM D2837

Material Type High density polyethylene (HDPE) | Polypropylene

Melt Flow Rate Test MethodASTM D1238Melt Flow Rate, maximum0.39 g/10 min

Mechanical Specifications

Minimum Bend Radius, unsupported 304.8 mm | 12 in

Tensile Property Test MethodASTM D638

Tensile Strength at yield, minimum 20.684 N/mm² | 3000 psi

Breaking Strength 90.718 kg | 200 lb

Pull Line Type Rope

Pulling Tension, maximum 229.064 kg | 505 lb

Environmental Specifications

Environmental Stress Crack ResistanceFailure rate of 10% within 96 hours **Environmental Stress Test Method**ASTM D1693, ESCR Condition B

Packaging and Weights

Weight, net 165.186 kg/km | 111 lb/kft

Regulatory Compliance/Certifications

Agency Classification

ISO 9001:2015 Designed, manufactured and/or distributed under this quality management system

* Footnotes

Environmental Stress Crack Resistance ESCR—Environmental Stress Crack Resistence

